

5F Annex Dragon Pearl Plaza
2123 Pudong Avenue
Shanghai 200135 - P.R. CHINA
Tél. : +86 21 68 55 50 32
Fax : +86 21 68 55 50 33
E-mail : ctcshanghai@ctcgroupe.com

Report No.: S181013967_1

31 October 2018

朱天宇 / 15726930231@163.com

APPLICANT: ZHEJIANG MENGTAI SPECIAL MATERIALS
TECHNOLOGY CO., LTD浙江蒙泰特种材料科技
有限公司 (C39251)
浙江嘉兴桐乡梧桐经济开发区齐鸣路270号
. ZHEJIANG
CHINA

Date of receipt : 25 Oct. 2018
Testing period : 25 Oct. 2018
: 30 Oct. 2018

Buyer: ---

Test(s) requested : ---
Service : REGULAR
Brand / Section : ---
Season : ---
End use : ---
Factory name : ---
Factory code : ---

For CE Marking : Yes


Previous report : ---
Product category : ---
Product type : ---
Test stage : FIRST TEST
Supplier name : ---
Exported to : ---

1. Conclusion:

	Tests description	Conformity
	EN 388	
1	Cut resistance : 2016	Level 2

Pass: requirements met Fail: requirements not met None: no requirement for this test N/A: not applicable

Approved by



Henry YAN
Laboratory Manager

Report No.: S181013967_1

31 October 2018

APPLICANT: ZHEJIANG MENGTAI SPECIAL MATERIALS
TECHNOLOGY CO., LTD 浙江蒙泰特种材料科技
有限公司 (C39251)

2. Sample(s) description assigned by laboratory:

<u>Size</u>	<u>Analyzed product</u>	<u>Description</u>	<u>Sample information</u>
	MATERIAL	Material	



181013967

Report No.: S181013967_1

31 October 2018

APPLICANT: ZHEJIANG MENGTAI SPECIAL MATERIALS
TECHNOLOGY CO., LTD浙江蒙泰特种材料科技
有限公司 (C39251)

3. MATERIAL/

Material

	Method	Client Requirement	Unit	Result	Conformity
(+) 4.1. Cut resistance : 2016	EN 388 : 2016				
Deviation from the test method				No	
used consumables - canvas				LEM 6	
used consumables - blade				OLFA RB45	
C1				1.2	
T1				8.9	
1C1				3.9	
I1				4.5	
C2				1.2	
T2				14.2	
1C2				6.4	
I2				4.7	
C3				1.2	
T3				6.9	
1C3				4.9	
I3				3.3	
C4				1.3	
T4				13.8	
1C4				5.8	
I4				4.9	
C5				1.2	
T5				16.2	
1C5				6.4	
I5				5.3	
Mean value of test piece 1				4.5	
C1 bis				0.9	
T1 bis				12.0	
2C1bis				6.4	
I1 bis				4.3	
C2 bis				1.2	
T2 bis				11.3	

Report No.: S181013967_1

31 October 2018

APPLICANT: ZHEJIANG MENGTAI SPECIAL MATERIALS
TECHNOLOGY CO., LTD 浙江蒙泰特种材料科技
有限公司 (C39251)

	Method	Client Requirement	Unit	Result	Conformity
2C2bis				4.4	
I2 bis				5.0	
C3 bis				1.2	
T3 bis				19.2	
2C3bis				4.9	
I3 bis				7.3	
C4 bis				1.3	
T4 bis				10.3	
2C4bis				4.3	
I4 bis				4.7	
C5 bis				1.2	
T5 bis				19.0	
2C5bis				4.9	
I5 bis				7.2	
Mean value of test piece 2				5.7	
Considered value				4.5	
Performance level				2	
Observation				First sequence Cn+1 higher than 3xCn, switch to EN13997	

END OF TEST REPORT

(+)CNAS accreditation

Table of Performance Level for Glove

Test Item	Performance Level					
	0##	1	2	3	4	5
Blade Cut Resistance (EN 388) Index (I) (minimum)	<1.2	1.2	2.5	5.0	10.0	20.0

Performance level 0 means the glove falls below the minimum performance level for the given individual hazard